
# HiFluxx ST704

Nitrogen Membrane Module



Parker hollow-fibre membrane modules produce nitrogen gas from compressed air to offer a costeffective, reliable and safe alternative to traditional cylinder or liquid nitrogen gas supplies.

Nitrogen is used as a clean, dry, inert gas primarily for removing oxygen from products and/or processes.

Parker modules can be built into a custom-made nitrogen generator or can be integrated with your (production) process to provide an on-demand, continuous source of nitrogen gas. Gas which can be used in a wide range of industries including food, beverage, pharmaceutical, laboratory, chemical, heat treatment, electronics, transportation, oil & gas, mining and marine.



# **Contact Information:**

Avilo Stikstof en Persluchtsystemen B.V.

Watertoren 41e 3247 CL Dirksland The Netherlands

Tel: +31 (0)187 48 13 66 Email: info@avilo.nl Website: www.avilo.nl

## Official Parker Distributor

Avilo is a worldwide supplier of parker membranes.
Always in stock. Fast delivery

## **Benefits:**

flow

- Less membrane modules needed per nitrogen system
  - More nitrogen per fibre is produced from Parker hollow-fibre membranes than any other in the world
- Use of low pressure standard industrial compressor
   No high pressure compressor needed to obtain required nitrogen
- Energy savings
   Operation at a low pressure requires less energy
- Reduced CO<sub>2</sub> emissions
   No heater required to open polymer membrane structure, thus reducing the energy consumption
- Robust fibre
   Most tolerant fibre to particle contamination
- Large membrane diameter
   Lowest membrane module pressure
   drop

- Strong engineering plastic Life-expectancy of more than 10 years
- Factory membrane ageing, pre-delivery
   No performance decrease over time due to fibre ageing
- Quick start-up time
   Required nitrogen purity is
   produced instantly, no time needed
   to heat-up
- Flexible mounting arrangements
   Can be mounted horizontal
   or vertical
- Low noise operation
   Radiated noise generated by membrane technology is extremely low
- No maintenance required No user serviceable parts
- Small system footprint
   Less modules needed to
   produce nitrogen requirements





### Performance data

Nitrogen	Minimum nitrogen <sup>1</sup> flow rate in m³/hr ² (CFM)²				
Purity %	99	98	97	96	95
4 bar g	0.25	0.52	0.79	1.05	1.30
(58 psi g)	(0.15)	(0.31)	(0.47)	(0.62)	(0.77)
5 bar g	0.37	0.73	1.09	1.42	1.75
(72.5 psi g)	(0.22)	(0.43)	(0.64)	(0.84)	(1.03)
6 bar g	0.47	0.92	1.37	1.81	2.26
(87 psi g)	(0.27)	(0.54)	(0.81)	(1.07)	(1.33)
7 bar g	0.65	1.16	1.67	2.18	2.69
(101.5 psi g)	(0.39)	(0.69)	(0.99)	(1.28)	(1.58)
8 bar g	0.72	1.33	1.95	2.50	3.05
(116 psi g)	(0.42)	(0.78)	(1.15)	(1.47)	(1.8)
9 bar g	0.87	1.55	2.22	2.86	3.50
(130.5 psi g)	(0.51)	(0.91)	(1.31)	(1.68)	(2.06)
10 bar g	0.96	1.72	2.47	3.19	3.90
(145 psi g)	(0.57)	(1.01)	(1.46)	(1.88)	(2.29)
11 bar g	1.05	1.89	2.73	3.51	4.30
(159.5 psi g)	(0.62)	(1.11)	(1.61)	(2.07)	(2.53)
12 bar g	1.14	2.05	2.97	3.83	4.69
(174 psi g)	(0.67)	(1.21)	(1.75)	(2.25)	(2.76)
13 bar g	1.22	2.22	3.21	4.14	5.07
(188.5 psi g)	(0.72)	(1.3)	(1.89)	(2.44)	(2.99)

Nitrogen	Feed-air consumption at minimum nitrogen flow rate in m³/hr² (CFM)²				
Purity %	99	98	97	96	95
4 bar g	2.32	2.81	3.21	3.53	3.87
(58 psi g)	(1.37)	(1.66)	(1.89)	(2.08)	(2.28)
5 bar g	3.08	3.71	4.21	4.58	4.96
(72.5 psi g)	(1.81)	(2.18)	(2.48)	(2.7)	(2.92)
6 bar g	3.67	4.47	5.12	5.65	6.21
(87 psi g)	(2.16)	(2.63)	(3.01)	(3.32)	(3.65)
7 bar g	5.08	5.54	6.09	6.66	7.26
(101.5 psi g)	(2.99)	(3.26)	(3.59)	(3.92)	(4.27)
8 bar g	5.60	6.35	7.08	7.61	8.21
(116 psi g)	(3.29)	(3.73)	(4.17)	(4.48)	(4.83)
9 bar g	6.77	7.36	8.08	8.70	9.41
(130.5 psi g)	(3.99)	(4.33)	(4.75)	(5.12)	(5.54)
10 bar g	7.51	8.20	9.03	9.71	10.5
(145 psi g)	(4.42)	(4.83)	(5.31)	(5.72)	(6.18)
11 bar g	8.26	9.06	9.99	10.7	11.6
(159.5 psi g)	(4.86)	(5.33)	(5.88)	(6.31)	(6.82)
12 bar g	9.05	9.91	10.9	11.8	12.7
(174 psi g)	(5.33)	(5.83)	(6.42)	(6.92)	(7.48)
13 bar g	10.1	10.9	11.9	12.9	14.0
(188.5 psi g)	(5.94)	(6.42)	(7.03)	(7.62)	(8.25)

Maximum pressure drop <0.3 bar (4 psi)

Maximum nitrogen flow rate = minimum flow rate + 30%

Values between brackets are indicative imperial values

## **Ambient Conditions**

Ambient temperature	+2°C to +50°C (+36°F to +122°F)
Ambient pressure	atmospheric
Air quality	clean air without contaminants

#### Material

Housing	Steel
Tube	Aluminum
Coating (housing)	ESPC to RAL 7035 (Light Grey)
Coating (tube)	None

## **Feed-air Conditions**

Maximum operating pressure	13.0 bar g (189 psi g)	
Min. / Max. operating temperature	+2°C to +50°C (+36°F to +122°F)	
Maximum oil vapour content	<0.01 mg/m³ (<0.01 ppm (w))	
Particles	filtered at 0.01 µm cut off	
Relative humidity	<100% (non condensing)	

# Services Available on Request

Weight, Dimensions and Connections

3D model CAD STEP file	
Test Report	

## Flow Rate Corrections

Nitrogen flow rate at feed temperatures other than 20°C (68°F)	Use bulletin S3.1.059*
Feed-air consumption at feed-air temperatures other than 20°C (68°F)	Use bulletin S3.1.059*

humidity <100% (non condensing)

Dimensions H x W x D	804 x 80 x 63 mm (31.7" x 3.15" x 2.48")
Weight	3.2 kg (7 lb)
Connection feed-air	G <sup>3</sup> / <sub>8</sub> " female to ISO 228
Connection nitrogen enriched air	G <sup>3</sup> / <sub>8</sub> " female to ISO 228
Connection oxygen enriched air at atmospheric pressure	G <sup>3</sup> /8" female to ISO 228
Dimensional drawing	Refer to K3.1.381
Part Number	159.005535

#### Note

Parker membrane systems produce both nitrogen and oxygen enriched air. Nitrogen enriched air can cause suffocation and oxygen enriched air causes increased fire hazards. The oxygen enriched air is available at ambient pressure and pressure build-up of enriched oxygen at the outlet must be prevented, otherwise a serious (reversible) decrease in performance will result. The nitrogen enriched air produced should be treated as pressurised air.

# For more information please visit www.avilo.nl

Parker has a continuous policy of product development and although the company reserves the right to changes specifications, it attempts to keep customers informed of any alterations.

©2014 Parker Hannifin Corporation. All rights reserved.

Catalogue: S3.1.260a 06/14





Parker membranes separate oxygen from pressurised air. The composition of the product is determined by measuring the residual oxygen content. The nitrogen content is calculated by subtracting the residual oxygen content from 100 %. Air is composed of nitrogen (78.1%), oxygen (20.9 %), Argon (0.9 %),  $CO_2$  (0.03 %), and some trace inert gases. Remember that the value that is normally called the nitrogen content actually is the inert gas content.

 $<sup>^2~</sup>$  m³/hr (CFM) refers to conditions at 1013 mbar(a) (14.7 psi a) and 20°C (68°F)  $^{\circ}$ 

<sup>\*</sup> Revision number may vary, make sure to use the most recent revision.